

1 WHAT IS CLAIMED IS:

2

3 1. A thermoplastic resin composition comprising a  
4 polyamide resin component composed of 5 to 95% by weight  
5 of the following component (A) and 95 to 5% by weight of  
6 the following component (B):  
7 Component (A): a polyamide resin obtained by  
8 polycondensing diamine(s) including at least  
9 tetramethylenediamine with dicarboxylic acid(s) including  
10 at least adipic acid; and  
11 Component (B): a polyamide resin obtained by  
12 polycondensing diamine(s) including at least one of 1,9-  
13 nonanediamine and 2-methyl-1,8-octanediamine with  
14 dicarboxylic acid(s) including at least terephthalic acid.

1 2. The thermoplastic resin composition according to  
2 Claim 1, wherein the polyamide resin component is composed  
3 of 55 to 80% by weight of the component (A) and 45 to 20%  
4 by weight of the component (B).

1 3. The thermoplastic resin composition according to  
2 Claim 1 or 2, wherein the component (A) is composed of a  
3 polyamide 4,6 resin obtained from tetramethylenediamine  
4 and adipic acid.

1 4. The thermoplastic resin composition according to  
2 any one of Claims 1 to 3, wherein the component (B) is

